

# ALGIZID-FUNGIZID-LÖSUNG

VOC-freie, AF-Lösung, wässrig, für aussen

Technical information Version  
(1.0) 02/26

Mauerwerk, Fassaden und Aussenanstriche werden durch Moos, Algen, Flechten und Pilzen bewachsen. Bei Renovationsanstrichen sind diese vorgängig zu entfernen, da sie den neu aufgetragenen Anstrich leicht durchwachsen können. Auch ungestrichene Flächen sind aus ästhetischen Gründen von derartigem Bewuchs zu befreien.

## Beschreibung

**Areas of application** Vor Anwendung sind die zu behandelnden Flächen von oberflächlichem Moos-, Algen- und Flechtenbefall zu reinigen/entfernen. Hierzu wird die Hochdruckreinigung empfohlen, gegebenenfalls unter Mitwirkung mechanischer Hilfsmittel.

## Core data

<b>Properties</b>	<b>Delivery viscosity</b>	Liquid
	<b>Density</b>	Approx. 1 kg/l
	<b>Storage life</b>	Store in tightly closed original container for 1 year at 5 - 25°C.
	<b>Processing temperature</b>	Do not process below + 5°C (object temperature), ideal temperature range 15 - 22°C.  Protect from direct sunlight.

## Substrate / Processing

<b>Application</b>	<b>Brushing and rolling</b> Unverdünnt
	<b>Airless spraying</b> Unverdünnt
<b>Coverage</b>	8 – 11 m <sup>2</sup> /kg Der Verbrauch ist von der Applikationsart, der Struktur des Untergrundes und der erzielten Schichtdicke abhängig. Die angegebenen Werte sind Durchschnittszahlen aus der Praxis.
<b>Tool cleaning</b>	Immediately wash out thoroughly with water, possibly with soft soap. Remove dried layers with nitro thinner.

## Information

Hazard warnings	For further information see the corresponding EU safety data sheet.
Further information	The SMGV information sheets and the FSO guidelines must be observed.
Important	<ul style="list-style-type: none"><li>▪ Haut und Augenkontakt vermeiden.</li><li>▪ Gummihandschuhe und Schutzbrille tragen.</li><li>▪ Keine Metallgefäße verwenden.</li><li>▪ Umliegende Nutzpflanzen möglichst abdecken.</li><li>▪ Bei Hochdruckreinigung eines WDVS-Fassadensystems ist der Druck anzupassen. Nach erfolgter Hochdruckreinigung, Fassade austrocknen lassen (maximale Objektfeuchtigkeit: 12%). Anschliessend Algizid-Fungizid Lösung satt auftragen und eintrocknen lassen (nicht nachwaschen). Fassade austrocknen lassen (maximale Objektfeuchtigkeit: 3%). Bei saugfähigen Untergründen anschliessend Dolwafix WV applizieren.</li></ul>

## Quality and environment

swiss  quality

Dold AG was founded on August 01, 1921 by Hans Dold in Wallisellen. Until Dold is still located at the same site and is one of the leading paint and varnish manufacturers in paint manufacturers in Switzerland. In Wallisellen, Dold AG develops and manufactures its innovative range of paints and varnishes for the construction painter as well as for industrial customers.



Swiss paint and varnish factory certified according to ISO 9001 / 14001 / 45001. Dold AG is one of the few one of the few paint and varnish factories which not only has its quality management, management, but also its environmental management system, as well as the occupational safety and health protection processes have been certified. These certifications are a clear commitment for Dold AG towards all its commitment to all its stakeholders.



Environmentally friendly products are a concern for DOLD. The foundation KMU Clima confirms Dold AG's contribution to voluntary climate protection. For this concern all direct emissions of CO<sub>2</sub> in form of electricity, heating and mobility are compensated by DOLD to a reforestation project in Uruguay. This is a long-term contribution to climate protection and for the sake of the environment.

The above information is for general guidance only. The working conditions beyond our control and the large number of different substrates mean that no claims can be made on the basis of this information. In case of doubt, we recommend that you carry out sufficient tests yourself. A guarantee can only be given for the consistently high quality of our products. All previous editions of this data sheet hereby lose their validity.